

WP/OFF

WP/FiberGlass + WallSilk®SOL

Tipo di supporto/ Support	Fibra di vetro/ Glass fiber
Versione/ Version	Tramata/ Textured
Protettivo/ Protective	2 mani di WallSilk®SOL/ 2 coats of WallSilk®SOL
Adatto per/ Suited for	Esterni/ Outdoor walls
Larghezza telo / Roll height	94 cm
Peso / Weight	260 g/m²

ITA

Il sistema **WP/OFF** è frutto di un'accurata ricerca tecnica per portare la forza decorativa delle immagini **WallPepper®** anche in ambienti esterni a contatto con acqua; è composto da speciali teli tecnici in fibra di vetro ad alta densità **WP/FiberGlass**, dal protettivo bicomponente poliuretanico a solvente **WallSilk®SOL**, trasparente e resistente all'acqua, alle piogge acide e ai raggi ultravioletti, e da una colla **silanica** altamente resistente all'acqua.

Il sistema **WP/OFF** è indicato per essere applicato **sulle pareti esterne** e in tutti quegli ambienti ove ci sia contatto, anche prolungato, con **acqua** corrente.

WP/FiberGlass

I teli tecnici **WP/FiberGlass** sono ecologici, in **tessuto di fibra di vetro** a trama intrecciata, **inodori, imputrescenti, traspiranti** e certificati in classe **B-s1,d0** per la resistenza al fuoco.

Sono facili da posare con il sistema della **colla a muro** grazie ai teli da 94 cm già tagliati a filo senza sormonto.

I teli tecnici a trama intrecciata sono molto resistenti a **urti, strappi, abrasioni** e, grazie alla loro stabilità dimensionale, garantiscono un'azione di consolidamento della parete proteggendola da fessurazioni e crepe di assestamento attenuando le disomogeneità.

WallSilk®SOL

È un protettivo opaco, poliuretanico **bicomponente** e trasparente alifatico a solvente, da utilizzare in combinazione con i nostri materiali che conferisce eccellenti caratteristiche di **idrorepellenza, ottima resistenza agli agenti atmosferici** ed incrementa notevolmente la **resistenza meccanica, la resistenza ai graffi, allo sfregamento**, rendendo possibile una pulizia profonda anche con detergenti professionali.

Dopo 12-36 ore dalla prima applicazione è possibile effettuare un'ulteriore mano di ricopertura. La completa essiccazione avviene in 24h, le proprietà chimico-fisiche e di resistenza saranno a regime dopo 48h.

ENG

The **WP/OFF** system is the result of a careful technical research to bring the decorative power of the **WallPepper®** artworks also in outdoor areas in contact with running water; the system is composed of the special technical fabrics **WP/FiberGlass** in high-density glass fiber, the two-component polyurethane protective solvent based **WallSilk®SOL**, which is clear and resistant to water, acid rain and ultraviolet rays, and an innovative **silanc glue** with superior water resistance.

The **WP/OFF** system is recommended for **outdoor installation** and in all those environments in direct contact with falling waters.

WP/FiberGlass

The **WP/FiberGlass** technical sheets are ecological, in **woven glass fiber, odorless, mold-proof, breathable** and certified in class **B-s1,d0** for fire resistance.

They are easy to lay with the **wall glue** system thanks to the 94 cm sheets already cut flush without overlap.

The technical sheets (especially with woven weft) are very resistant to **impacts, tears, abrasions** and, thanks to their dimensional stability, they guarantee a consolidation action of the wall protecting it from cracks and settlement cracks, attenuating the inhomogeneities.

WallSilk®SOL

It's a matt, **two-component** solvent based transparent polyurethane protective coating, to be used in combination with our materials that gives excellent **water repellency, excellent resistance to atmospheric agents and greatly increases mechanical resistance, scratch resistance and rubbing**, allowing deep cleaning even with professional detergents.

Its formulation doesn't contain polluting elements and after 12-36 hours from the first application it is already possible to perform a further covering coat. The complete drying takes place in 24h and the chemical-physical properties of resistance will be fully operational after 48h.



B-s1,d0
EN13501-1/07



Idrorepellente/
Waterproof



Resistente
all'abrasione
/ Abrasion
Resistant



Resistente alle
macchie / Stain
Resistant

Resistenza ai lavaggi e alle macchie*

Resistance to washing and stains*

I trattamenti della linea **WallSilk*** sono studiati per la protezione di superfici di design che resistano nel tempo garantendo la performance tecnica per oltre 5 anni adottando alcune semplici precauzioni, tra cui:

• Sottoporre a stress la superficie solo dopo 72 ore dalla posa.

• Pulizia con prodotti adatti

Le superfici in resina sono molto resistenti e, per tanto, possono sopportare la saltuaria pulizia con prodotti aggressivi.

La quotidiana pulizia è possibile con normali detergenti neutri diluiti con acqua, si sconsiglia l'uso quotidiano di prodotti acidi, alcolici o granulosi.

• Ripristino delle proprietà di impermeabilizzazione e resistenza chimico/meccanica.

Eventualmente è possibile ripristinare le caratteristiche originarie di resistenza chimico/meccanica e, soprattutto, di impermeabilizzazione in modo semplice riapplicando una mano di trattamento bicomponente sulla superficie.

WP/OFF

The **WallSilk*** coatings line is designed to protect design surfaces that last over time guaranteeing technical performance for more than 5 years with simple precautions, including:

• Stress the surface only after 72 hours.

• Cleaning with suited products

Resin surfaces are very resistant and, therefore, they can withstand occasional cleaning with aggressive products.

Daily cleaning is possible with normal neutral detergents diluted with water, we advise against daily use of acidic, alcoholic or grainy products.

• Restoration of waterproofing and chemical/mechanical resistance properties.

It is possible, eventually, to restore the original features of chemical / mechanical resistance and, above all, waterproofing in a simple way by reapplying a two-component treatment coat on the surface.

Agente pulente o macchiante	Tempo di contatto prima del lavaggio	Valutazione Finale
Acqua Distillata	24 h	5
Detergente Generico	24 h	5
Olio d'Oliva	24 h	5
Latte	24 h	5
Ammoniaca diluita al 10%	8 h	5
Cif Spray con candeggina	16 h	5
Viakal	16 h	5
Mastro Lindo	16 h	5
Acetone	120 s	4
Alcool Etilico diluito al 10%	24 h	4
Vino Rosso	24 h	4
Caffè	24 h	4
Tè	24 h	4
Cif Power Cream Cucina	16 h	4
Glassex con ammoniaca	16 h	4
Candeggina Ace	16 h	4
Alcool Denaturato	16 h	4
Lysoform Casa	16 h	4
Inchiostro Nero	24 h	3

Risultati

5 = Nessun cambiamento

4 = Lieve alone o segno appena visibile

3 = Lieve segno visibile da più direzioni

2 = Segno pronunciato

1 = Degrado superficiale o danno strutturale

*Test effettuati in laboratorio indipendente come da norme EN 13442 e EN 12720, conforme alla classificazione CEN/TS 16209, classe raggiunta, non accreditata, "E".

I test sono stati effettuati con sostanze a temperatura ambiente (20°C).

Cleaning or staining agent	Time spent before cleaning	Final Rating
Distilled Water	24 h	5
Cleaning Agent	24 h	5
Olive Oil	24 h	5
Milk	24 h	5
Ammonia 10% diluted	8 h	5
Cif Spray with bleach	16 h	5
Viakal limscale remover	16 h	5
Mr Clean	16 h	5
Acetone	120 s	4
Ethanol Alcohol 10% diluted	24 h	4
Red Wine	24 h	4
Coffee	24 h	4
Tea	24 h	4
Cif abrasive kitchen cream	16 h	4
Glassex with ammonia	16 h	4
Ace bleach	16 h	4
Denatured Alcohol	16 h	4
Disinfectant floor cleaner	16 h	4
Black Ink	24 h	3

Rating

5 = No change

4 = Light halo or barely visible mark

3 = Light mark visible from multiple directions

2 = Strong mark

1 = Surface degradation or structural damage

*Tests carried out in an independent laboratory as per EN 13442 and EN 12720 standards, compliant with CEN / TS 16209 classification, achieved class, not accredited, "E".

All substances have been tested at room temperature (20°C)